

Fier me, 19/09/2022

TREGUESIT TEKNIK TE TUBOVE PREJ BETONI, BETONI/ARME			BASHKIA FIER							
Nr Karakteristikat Teknike	Njesia	TUBO BETON/ARME(ME HEKUR)								
		DIAMETRI								
		Φ300mm	Φ400mm	Φ500mm	Φ600mm	Φ800mm	Φ1000mm	Φ1500mm	Φ2000mm	
1	2	3	4	5	6	7	8	9	10	11
1	Diametri i brendshem	mm	300	400	500	600	800	1000	1500	2000
2	Trashesia e mureve	mm	50±3	50±3	50±3	60±3	80±5	100±5	150±6	200±7
3	Gjatesia e Tubit	mm	1000+15	1000+15	1000+15	1000+15	1000+15	1000+15	1000+15	1000+15
4	Armatura e hekurit	kg								
	Armatura gjatesore		5Φ6	6Φ6	8Φ6	10Φ6	10Φ6	15Φ6	20Φ6	57Φ6
	Armatura terthore		10 Φ5.5	11Φ5.5	13Φ5.5	13Φ5.5	13Φ6	13Φ6	13Φ6	26Φ6
5	Marka e betonit Mpa jo me e vogel	Mpa	20	20	20	20	20	20	20	20
6	Rezistenca ne shtypje te brendshme Mpa	Mpa	0,05	0,05	0,05	0,05	0,05	0,05	0,05	0,05
7	Ujethithja ne % jo me shume se	%	6	6	6	6	6	6	6	6
8	Ngarkesa e shkaterrimit kN/ml tub	kN/ml tub	34,00	42,00	54,00	63,00	77,00	92,00	132,00	172,00

TUBOT E BETONIT DUHET TE JENE SIPAS STANDARTIT SHQIPTAR S SH 518:1987

Materialet per prodhimin e tubove te betonit duhet te jete si me poshte :

- S SH EN 197-1:2011 CIMENTO.
- S SH 505:1987 RERE PER PUNIME NDERTIMI
- S SH 504:1987 ZALL PER PUNIME NDERTIMI
- S SH 509:1987 CAKELL PER PUNIME NDERTIMI
- S SH 2751:1987 UJE PER PERGATITJE E BETONIT DHE LLACIT

Drejtoria e Puneve Publike

Silvana Basha

Sokol Krasniqi



Drejtoria e Pergjithshme e Puneve Publike, Hartimit projekteve e Infrastruktures

Gazmira Plesati


